

Sigma Stretch Film

General Specifications

GRADE: World Wrap Hand Film

TYPE: CAST HIGH QUALITY

TEST	80 Gauge	ASTM TEST METHODS
TENSILE TEST TENSILE @ YIELD MD TENSILE @ YIELD TD	1350 PSI 1,300 PSI	D-882
TENSILE STRENGTH MD TENSILE STRENGTH TD	5,100 PSI 3,900 PSI	
ELONGATION MD ELONGATION TD	320% 700%	
TEAR TEST ELMENDORF MD ELMENDORF TD	40 G / MIL 850 G / MIL	D-1922
PUNCTURE TEST FORCE ENERGY ENERGY / THICKNESS	10.1 LBS 21.6 IN-LBS 27.0 IN-LBS/MIL	D-4649 A5
OTHER YIELD	37,500 SQ.IN/LB	

Note: MD = Machine Direction TD = Tranverse Direction

Made in Canada by

Sigma Stretch Film of Canada

219 Jamieson Bone Road Belleville, Ontario K8N-5A5
 Phone: 866-848-4400 · 613-966-4400 · Fax: 613-966-2781

Email: sigma.stretch@sigmaplastics.com

Visit our website at www.sigmastretchfilm.com